



# TECHNICAL DATA SHEET

**Tremco DualFlex®**

Flashing Material for  
Waterproofing Membranes

## PRODUCT DESCRIPTION

Tremco DualFlex® is a reinforcing flashing that consists of a central strip of elastomeric SEBS rubber flanked on either side by an absorbent nonwoven felt. The felt allows for easy integration of the flashing and the waterproofing membrane. The elastomeric SEBS rubber provides superior movement capability without compromising the waterproofing.

## BASIC USES

Tremco DualFlex is used as a flashing material at joints, transitions in plane, horizontal-to-vertical transitions, and any other situation in waterproofing where durable, reinforcing sheeting is desired. Tremco DualFlex is ideal for use with TREMproof® hot-applied waterproofing membranes, Vulkem® deck coating basecoats, Vulkem® EWS coating systems, and TREMproof® PUMA below grade waterproofing systems.

## AVAILABILITY

Immediately available from your local Tremco Sales Representative or Tremco Distributor. For distributor locations, visit [www.tremcosealants.com](http://www.tremcosealants.com).

## PACKAGING

9.5" x 98' (240 mm x 30 M) rolls

6" x 98' (150 mm x 30 M) rolls

19" x 98' (480 mm x 30 M) rolls

## FIRE RATED SYSTEMS

None presently listed. For firestop engineering judgement requests, please visit [www.tremcosealants.com](http://www.tremcosealants.com) or contact Tremco Technical Services at 866-209-2404.

## LIMITATIONS

- Not for use with TREMproof® 201/60 or TREMproof 250GC cold fluid-applied waterproofing membranes.

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES US	TYPICAL VALUES SI
Color		Gray	
Resistance to Temperature min/max		-22 °F to 194 °F	-30 °C to 90 °C
Breaking Load Longitudinal	DIN EN ISO 527-3		251 N / 15 mm

## TYPICAL PHYSICAL PROPERTIES

Breaking Load Lateral	DIN EN ISO 527-3	24 N / 15 mm
Extension Break Longitudinal	DIN EN ISO 527-3	32%
Extension Break Lateral	DIN EN ISO 527-3	122%
Resistance to Water Pressure	DIN EN 1928 (Version B)	> 21.7 psi > 1.5 psi
UV Resistance min	DIN EN ISO 4892-2	500 h

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**NOTE:** All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

DUALFLEXDS/1122

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



*Construction Products Group*

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)